

REMARKS

Favorable consideration of this application, as presently amended, is respectfully requested.

The attached replacement sheet for page 47 of the specification corrects a typographical error made in the replacement sheet previously submitted with the preliminary amendment filed on October 9, 2003.

The present application is believed to be in condition for a full and thorough examination on the merits. An early and favorable consideration of the present application is hereby respectfully requested.

Respectfully submitted,

OBLON, SPIVAK, McCLELLAND,
MAIER & NEUSTADT, P.C.



Gregory J. Maier
Attorney of Record
Registration No. 25,599

Customer Number

22850

Tel: (703) 413-3000
Fax: (703) 413 -2220
(OSMMN 08/03)

Surinder Sachar
Registration No. 34,423

GJM/SNS/STD/mac
I:\ATTY\STD\24's\243760US2\243760US.PREL AM.DOC

Table 1

	Measure- ment 1	Measure- ment 2	Measure- ment 3	Measure- ment 4	Measure- ment 5	Measure- ment 6	Measure- ment 7	Measure- ment 8
	Stacked thickness (μm)	Ratio of the apparent thickness to the initial thickness of the electrode	Amount of the electrolyte (g)	Initial expansion rate	Capacitance (F)	Resistance ($\text{m}\Omega$)	Retention voltage (V)	Expansion rate after charging and discharging
Ex. 1	735	1.021	111	1.13	1650	2.21	2.444	1.15
Ex. 2	760	1.056	115	1.13	1550	2.41	2.451	1.15
Ex. 3	780	1.054	109	1.11	2210	3.22	2.391	1.48
Ex. 4	790	1.068	112	1.11	2180	3.31	2.401	1.51
Ex. 5	780	1.055	117	1.13	1570	2.33	2.460	1.16
Ex. 6	725	1.007	100	1.11	1619	3.53	2.055	1.12
Ex. 7	736	1.022	113	1.13	1650	2.18	0.507	$\frac{1.15}{1.115}$
Comp. Ex. 1	720	1.000	79	1.11	1412	5.42	0.221	1.11
Comp. Ex. 2	737	1.024	75	1.01	890	20.8	0.011	1.05